

## **GOLDSEAL GROUP**

**Rust Proof Services NZ (2005) Ltd**  
40 Northway Street,  
Hamilton, New Zealand.  
P O Box 20466, Te Rapa.  
Telephone: 07 849 9253  
Mobile: 0276 315 657  
rustproofservices@goldseal.co.nz



### **SPECIFICATIONS**

#### **SILVERSEAL “80” FINISH COAT**

Description:	A blend of styrene modified co polymer type resins, compounds, oils and solvents giving a semi gloss coating of silver grey appearance and designed for use on rusty structural steel and corrugated iron roofs.
Preparation:	All scale rust and grime to be removed by chipping and/or wire brushing to leave a clean dry surface. If surfaces have been exposed to salt water spray they should be washed thoroughly with fresh water to remove contamination. This surface should then be treated by a phosphoric acid type preparation and allowed to dry thoroughly before applying one coat of RUST PROOF SERVICES STEELCOTE primer.
Application:	By airless spray equipment (Wagner or Aro) tip size 015-017 max pressure 2500 psi (Not suitable for roller or brush application)
Coverage:	5 m2 per litre will provide coating of up to 150 microns and 2 coats are considered sufficient for most works
Drying Time:	4 hours between coats
Solvents:	Shell Sol 664 (clean up only - thinning not required)
Flash Point:	30c (during application only)
Flammable Rating:	3B
Colour:	Silver Grey
Availability	20 Litre Packs